



SCHEDA TECNICA
INDUSTRIA CONCIARIA E DEI SINTETICI

articolo Lamina totale ad elevata brillantezza, media coprenza su pellame trattato.

caratteristiche tecniche Studiata per applicazione su articoli bottalati e nappe. L'elasticità del prodotto è tale da consentire risultati eccellenti in termini di compattezza, brillantezza e nitidezza del colore. Offre ottimi risultati in termini di tenuta e resistenze superficiali.

condizioni di stampa e misure Temperatura di stampa: 90°C/105°C.
Pressione: 50-60 kg/cm².
Tempo di sosta: 3-6 secondi.
Larghezza: 1000-1600mm.
Lunghezza standard bobine: 250metri.
Anima: 75mm.
Spessore: 19my.

informazioni utili Utilizzare pretrattamenti specifici di resine da applicare sul pellame prima dell'applicazione del transfer.
Rimuovere il supporto plastico dal pellame stampato almeno 6-8 ore dopo la stampa del transfer in modo da evitare traumi al prodotto con uno shock termico troppo repentino.
Limitare l'utilizzo di solventi durante la preparazione del pellame destinato ad articoli laminati e durante le fasi successive alla applicazione della lamina.

colorazioni Selection 1-7 cartella colori "Industria Conciaria".

Web site: www.stampfoil.it
Email: info@stampfoil.it





TECHNICAL DATA SHEET TANNING AND SYNTETHIC INDUSTRY

article Lamina for total application with high brightness, medium coverage on treated leather

technical properties Designed to realize milled and "nappa" effect articles. Its elasticity allows to reach excellent results in terms of compactness, brightness and sharpness of the color. It offers excellent results in terms of surface resistences.

stamping conditions and roll format Stamping temperature: 90°C/105°C.
Pressure: 50-60 kg/cm².
Dwell time: 3-6 seconds.
Width: 1000-1600mm.
Standard roll lenght: 250metri.
Core: 75mm.
Thickness: 19my.

useful informations Use specific pre-treatments of resins on leather before applying the transfer. Remove the plastic support from the printed leather at least 6-8 hours after the application of the transfer in order to avoid thermal shock. Limit the use of solvents during the preparation of the leather used for laminated articles and during the following phases after the application of the transfer.

colors Selection 1-7 color chart "Industria Conciaria"

Web site: www.stampfoil.it
Email: info@stampfoil.it

